

NEOFLON ETFE EP-620

NEOFLON ETFE EP-620 is a resin with excellent flexibility and stress crack resistance. It is suitable for extrusion molding, injection molding and wire coating

Typical properties

Melt Flow Rate	g/10 min	9 - 18	ASTM D-3159
Melting Point (DSC)	°C	218 - 228	ASTM D-3159
Tensile Strength	MPa	28 - 33	ASTM D-3159
Elongation	%	300 - 400	ASTM D-3159
Specific Gravity	-	1,83 - 1,88	ASTM D-3159

Note: Typical properties are not suitable for specification purpose

Typical applications

- Wire coating
- Films and sheets

Packaging

NEOFLON ETFE pellets are packaged in 25 kg aluminium laminated bags

Important Notice

The information contained herein is based on technical data and tests we believe to be reliable and is intended for use by persons having technical knowledge and skill, solely at their own discretion and risk. Since conditions of use are outside of our control, we assume no responsibility for results obtained or damages incurred through application of the data given. The publication of the information herein shall not be understood as permission or recommendation for the use of our fluorocarbon compounds in violation of any patent or otherwise. We only warrant that the product conforms to description and specification, and our only obligation shall be to replace goods shown to be defective or refund the original purchase price thereof.

USE OF PRODUCT: The product is for the industrial use only. We do not guarantee the safety in case the product is used for the other purposes. When using the product for health-care application or for food/feed application, consult us in advance.

MEDICAL USE: These products are not specifically designed or manufactured for use in implantable medical and/or dental devices. They have not been tested for such applications and will only be sold for such use pursuant to contract containing specific terms and conditions required by us.

Daikin Chemical Europe GmbH
Am Wehrhahn 50
40211 Düsseldorf
Germany
Phone: +49-211-1792250
Fax: +49-211-1640732
www.daikinchem.de

Daikin Industries, Ltd.
Umeda Center Building
2-4-12 Nakasaki-Nishi, Kita-ku
Osaka 530-8323, Japan
Phone: +81-6-6374-9355
Fax: +81-6-6374-4281
www.daikin.com

Daikin America, Inc.
20 Olympic Drive
Orangeburg, NY 10962
USA
Phone: +1-845-365-9500
Fax: +1-845-365-9515
www.daikin-america.com